

Update: 28/03/2022	TECHNICAL DATA SHEET	
Ref: Wire	Solder Wire	
Created on: 03/05/2001	Pb93.5Sn5Ag1.5 CT2	



GENERAL CHARACTERISTICS:

High melting point (HMP) solders wire, with incorporated flux for soldering equipment in electronics.
Conforms to standards ISO 9453 : alloy n° 191 and is also J-STD 006 compliant.

CHEMICAL CHARACTERISTICS:

Amount of Tin : 5 % ± 0.2%
Amount of lead : Rest
Amount of Silver : 1.5% ± 0.3%
Tin-lead-silver double refined at first melting, with an overall purity of 99.6%
Type of cored flux : CT2
Amount of cored flux : available in 2.2% (standard). Other: consult us.

PHYSICAL AND CHEMICAL CHARACTERISTICS:

ALLOY : Pb93.5Sn5Ag1.5

Melting point : Solid 296°C to liquid 301°C
Specific weight : 11.04 g/cm³
Wire diameter : from 0.7mm to 5 mm

FLUX : CT2

Natural rosin.
Chloride content : 0.4 %
Acid value: 200 mgKOH/g
Fast soldering.
CT2 flux is classified 1.1.2 according to standard ISO EN 9454.
CT2 flux is an activated rosin flux.
CT2 is classified **ROL1** (J-STD-004)

USING CHARACTERISTICS:

Working temperature : 350°C to 460°C (typical)

PACKAGING / STORAGE:

Solder wire : Various types of reels available adapted to Customer's needs.
Depending on diameter and length.
Other product shape : On request
Storage : In original packaging at room temperature for 24 months.

SAFETY:

Material Safety Data Sheet available on request. Please consult it before use.

ADDITIONAL INFORMATION:

Quality Certificate available on request.

Our manufacturing processes have been Subjected to FMECA analysis (equivalent of AMDEC in France).



We cannot anticipate any and all conditions and situations under which the information and our products or the combination of both with others will be used. We do not assume any liability in the safety and suitability of our products alone or in combination with others. Users must make their own tests to determine the safety and suitability of each product used alone or with other products for their own use. Except any previous written agreement, our products are sold without guarantee and customers must assume all liability for any loss or damage suffered by themselves or by third parties, either from handling or use of our products alone or with others. In case of any difference or variation seen during the use of the products we request that you contact our technical department.